

# **Farbatone**

**Technical Data Sheet** 

**Screen Printing inks** 

Solvent Base

2020 24,Jan

Ink

# **RUB Series**

#### FIELD OF APPLICATION

### **Substrates**

The screen printing ink RUB is excellently suited to print onto PU leather **PVC** leather Genuine leather EVA (Split, Molded, Skin) **TPU** Polyester Wtaer Proof Nylon Nvlon

#### Field of Use

RUB series is designed to print on Flip flop, Hawai Chappal, Molded EVA Sleeper, EVA Sandals, EVA Shoes, EVA Yoga Mat, EVA Toys, Bagpack.

The ink can be used as 1 or 2 component ink.

This special ink has compared to other 2 component inks, a very good adhesion to the substrate and is highly qualified for footwear standard.

RUB can also be processed with spray gun, drawing brush on EVA material. In order to avoid surface irregularities, we recommend to filter the thinned ink (25 microns screen) before processing.

#### **CHARACTERISTICS**

This glossy, physically drying and chemical reactive screen printing ink exhibits good mechanical & chemical resistance as well as good flexibility and adhesion. Excellent printability and stable in color matching.

**HOW TO USE** 

Apply EVA Primer 2303 to EVA substrate by wiping to improve the mechanical strength of the ink. Dilute the ink with 10%-20% TP-65 (slow dry thinner) or TP-69 (medium dry thinner). Use TP-67 to make the the drying slower. You may add Hardener H/9004 Hardener to improve the mechanical strength of the ink on substrate. For Synthetic and Genuine leather always advisable to use as 2 component ink. Some PU material needs post treatment after

RUB is designed to dry slowly in order to avoid clogging.

For overprinting, the next color is printed only after tack free..

Mesh Recommended- 40T-120T

Tack Free Time	5-10 minutes	Natural Cure
Hard Drying Time	6-8 hours	Natural Cure

If several layers are printed longer drying time is recommended

#### **CLEANER**

Use TP-65 for cleaning the screen /washing up.

#### RANGE OF COLORS

#### **Basic Colors**

100 Transparent 105 H.D. White 201 Deep Yellow 203 Original Yellow 206 lemon yellow 300 Rose Red



# **Farbatone**

## **Technical Data Sheet**

### **Screen Printing inks**

2020 24,Jan

3020 Dark Red

3038 Light Resistant Magenta

304 Bronze Red

305 Orange

401 Violet

403 Original Blue

404 Ultra Marine

408 Emerald Blue

501 Black

601 Green

701 Brown

#### **Fluorescent Colors**

131 Fluorescent Yellow

133 Fluoroscent Red

134 Fluoroscent Orange

140 Fluoroscent Green

148 Fluoroscent Blue

141 Fluoroscent Violet

#### **Metallic Colors**

801 Silver

901 Pale Gold

902 Rich Gold

# **4 Color Process Printing inks**

**Process Black** 

**Process Red** 

**Process Yellow** 

**Process Blue** 

#### **ADDITIVES**

#### Thinner:

Before production, the viscosity of the screen printing has to adjusted by the addition of thinner.

Thinner, very fast (addition 15%-25%)

Thinner, standard (addition 15%-25%) TP-65

#### **Retarder:**

Thinner, slow( addition 15%-20%) TP-67

Retarder TP-67 can be used along with TP-65 or TP-61 to meet the printing requirement.

#### Hardener

Prior to printing hardener must be added in correct quantity and always by weight and mixture must be stirred thoroughly.

Hardeners are sensitive to humidity and always to be stored in a sealed container.

Hardener 9004 is the standard hardener -H

The two different ratio are

- 5% Hardener 9004/ H 20 parts by weight of ink + 1 part of hardener by weight
- 2) 10% Hardener 9004/ H 10 parts by weight of ink + 1 part of hardener by weight

The second variation must be applied if high resistance (e.g. dry & wet Test) is required.

#### **Custom Colors**

Pantone/RAL/TPX colors are custom made colors and can be developed as per request.

### **TYPE OF PACKING**

1-kg Can

#### SHELF LIFE

Shelf life depends on the reactivity of the

while adding hardener as well as storage conditions( temperature).

The shelf life for an unopened ink container if stored ink dark room at a temperature of 15°-25° C is



# **Farbatone**

## **Technical Data Sheet**

**Screen Printing inks** 

2020 24,Jan

- 1) 2 years for the basic colors and Process colors
- 2) 1 year for Metallics and fluorescent colors.

Under different conditions, particularly higher storage temperatures, the shelf life is reduced .In such case,the warranty given by Spinks expires.

#### **PRECAUTION**

- 1) Hardener 9004/H is the standard hardener .At room temperature 20°25°C a pot life is 4-5 hours. If temperature is higher shelf life of the ink will reduce.
- 2) Ink is glossy .Matt ink can be developed on request.
- 3) As PVC doesn't have good solvent resistance, it may cause tackiness problem while stacking Nylon material with PVC laminated from backside, make sure finished products are dried thoroughly and avoid stacking together. When printing on Nylon with backside laminated PVC, it is easy to cause color transformation, to solve this problem, use color with good penetration resistance.
- 4) Please refer MSDS before use.
- 5) Be sure to do trials before commercial run to confirm that the product fits the purpose
- Additional technical information may be obtained from our Technical Department.
- 7) All characteristics described in this Technical Data Sheet refer exclusively to the standard products listed under range, provided that they are processed in accordance with the intended use and only when used with

the recommended additives. The selection and testing of the ink for specific applications is exclusively your responsibility. Should, however, any liability claims arise, they shall be limited to the value of the goods delivered by us andutilized by you with respect to any and all damages not caused intentionally or by gross

Properties		
Items	Perform	
	ance	
Adhesion	Excellen	
	t	
Transfer	Grade	
resistance	4-5	
Scratch	Grade	
Resistance	4-5	
Anti-attrition	Grade	
	4-5	
Kneadability	Grade 5	
Acid Resistance	Grade	
	3-4	
Alkali	Grade	
Resistance	3-4	
Water	Grade	
Resistance	3-4	

Technical Parameters		
Items	Performanc	
	е	
Appearance	Refer to	
	color sample	
Chroma	8%-15%	
Thinness	Less than 7	
	microns	
Viscosity	100-180P	
Glossiness	70-75	
Flowability	15-20mm/s	
Resin	>45%	